

Fresh



nam SPORTS

Applications	Tennis, Multisports
Fibres	Polyethylene/ UV-stabilized/ Fibrilated ca. 100 µm thickness/ 8.800 dtex
Production method	Lineair tufting
Gauge	5/16"
# stitches / rm	ca. 190 / rm
# tufts / m ²	ca. 23.940 / m ²
# filaments / m ²	ca. 47.880 / m ²
Pile height	ca. 22 mm
Pile weight	ca. 1060 gr / m ²
Total weight	ca. 2220 gr / m ²
Tuft cloth	Polypropylene, ca. 160 gr / m ²
Backing	Latex, ca. 1000 gr / m ²
Infill	ca. 24 kg / m ² sand
Roll width	400 cm
Colour	Green/ Red
Colour fastness	Scale 7 (DIN 54004)
UV-stability	> 3.000 hours UV-A
Water permeability	6.10-4 m/sec

Namsports reserves the right to amend technical specifications on the above mentioned product.
Delivered products can slightly differ from these technical data.
Namsports guarantees the technical quality of the proposed article.